

TELECOMMUNICATION


STRANDS FOR SELF-SUPPORTING TELEPHONE AND OPTICAL FIBER CABLES

FGC, in partnership with the primary international manufacturers, has developed a great experience in the production of strands for self-supporting cables.

TECHNICAL FEATURES OF THE MATERIALS

GALVANIZED STEEL STRANDS

Characteristics	Value
Diameters	from 1,80 to 5,50 mm
Tensile strength	from 1400 to 1770 N/mm ²
MBL	> 300 daN
Standards and classes of coating	EN10244-2 Class A, AB and B
Standards	EN10264-2, EN50189




The material is strictly controlled during every stage of manufacturing according to our Quality System in compliance with **EN ISO 9001**.


CONSTRUCTIONS




1×3



1×7



1×12



1×19

PACKAGING

STRANDS

Wooden reels from 400 to 1500 kg

SEAWORTHY PACKING

Treated and fumigated wooden reels FAO ISPM 15

